

COLOROBRIA®

Floor Tiles Granular Glazes High Temperature

High Temperature Glossy Granular Glazes

High Temperature Matt Granular Glazes



High Temperature Spotted Effect Granular Glazes

High Temperature Glossy Granular Glazes

CODE	DESCRIPTION	GRANULOMETRY	Dilation Coeff. (x10 ⁻⁷)	FIRING TEMPERATURE	CYCLE
GFR-142	Glossy White	0,14 – 0,50	106	1170 – 1220 C	45' – 60'
GFR-144	Glossy White	0,05 – 0,14	106	1170 – 1220 C	45' – 60'
GFR-147	Glossy White	0,14 – 0,31	106	1170 – 1220 C	45' – 60'
GFM-2156	Flake effect Glossy White	0,14 – 0,72	62	1170 – 1220 C	45' – 60'
GFR-447	Semi-Glossy Transparent	0,14 – 0,31	62	1170 – 1220 C	45' – 60'
GFR-1087	Glossy Transparent	0,14 – 0,31	68	1170 – 1220 C	45' – 60'
GFRE-01/49	Luster	0,05 – 0,25	71	1170 – 1220 C	45' – 60'


N.B. : We recommend to perform always the preliminary tests before the production, since we are not responsible for the material accidentally damaged.
For any another technical information on the product, consult the corresponding safety data sheet.

High Temp. Matt Granular Glazes

CODE	DESCRIPTION	Granulometry	Dilation Coeff. (x10 ⁻⁷)	FIRING TEMP.	CYCLE
GFR-202	Yellowish Satin Matt	0,14 – 0,50	60	1170 – 1220 C	45' – 60'
GFR-477	Transparent Satin Matt	0,14 – 0,31	60	1170 – 1220 C	45' – 60'
GFR-487	Transparent hard Matt	0,14 – 0,31	60	1170 – 1220 C	45' – 60'
GFR-737	Semi-Transparent Satin Matt	0,14 – 0,31	65	1170 – 1220 C	45' – 60'
GFR-1118	Polishing Transparent Matt	0,08 – 0,14	57	1170 – 1220 C	45' – 60'
GFR-1176	Polishing Transparent Matt	0,10 – 0,20	63	1170 – 1220 C	45' – 60'
 GFR-1355	Matt	0,08 – 0,31	63	1180 – 1200 C	45' – 60'
 GFR-1356	Matt	0,08 – 0,25	63	1180 – 1200 C	45' – 60'

N.B. : We recommend to perform always the preliminary tests before the production, since we are not responsible for the material accidentally damaged.
For any another technical information on the product, consult the corresponding safety data sheet.

High Temp. Matt Granular Glazes

CODE	DESCRIPTION	Granulometry	Dilation Coeff. (x10 ⁻⁷)	FIRING TEMPERATURE	CYCLE
GFM-2095	Matt	0,14 – 0,31	63	1170 – 1220 C	45' – 60'
GFM-2144	Matt Flake Effect	0,05 – 0,14	62	1170 – 1220 C	45' – 60'
GFM-2146	Matt fine	0,05 – 0,10	60	1170 – 1220 C	45' – 60'
GFM-2148	Transparent Matt	0,14 – 0,31	60	1170 – 1220 C	45' – 60'
GFM-2149	White semi-matt	0,14 – 0,31	63	1170 – 1220 C	45' – 60'
GFM-2154	Matt	0,05 – 0,14	57	1170 – 1220 C	45' – 60'
GFM-2158	Hard semi-matt	0,05 – 0,14	57	1170 – 1220 C	45' – 60'
GFM-2159	Satin	0,08 – 0,14	57	1170 – 1220 C	45' – 60'
GFM-2183	Polishing Transparent Matt	0,05 – 0,31	55	1170 – 1220 C	45' – 60'
 GFM-2188	Sugar Matt	0,05 – 0,31	n.d.	1170 – 1220 C	45' – 60'

N.B. : We recommend to perform always the preliminary tests before the production, since we are not responsible for the material accidentally damaged.
For any another technical information on the product, consult the corresponding safety data sheet.

High Temp. spotted effect Granular Glazes

CODE	DESCRIPTION	Granulometry	Dilation Coeff. (x10 ⁻⁷)	FIRING TEMPERATURE	CYCLE
GRS-4301	Spotted effect Black	0,08 – 0,37	n.d.	1170 – 1220 C	45' – 60'
GRS-4311	Spotted effect White	0,08 – 0,37	n.d.	1170 – 1220 C	45' – 60'
GRS-4321	Spotted effect Blue	0,08 – 0,37	n.d.	1170 – 1220 C	45' – 60'
GRS-4331	Spotted effect Grey	0,08 – 0,37	n.d.	1170 – 1220 C	45' – 60'
GRS-4341	Spotted effect Dark Grey	0,08 – 0,37	n.d.	1170 – 1220 C	45' – 60'
GRS-4351	Spotted effect Green	0,08 – 0,37	n.d.	1170 – 1220 C	45' – 60'
GRS-4361	Spotted effect Dark Blue	0,08 – 0,37	n.d.	1170 – 1220 C	45' – 60'
GRS-4371	Spotted effect Red	0,08 – 0,37	n.d.	1170 – 1220 C	45' – 60'
GRS-4381	Spotted effect Pink	0,08 – 0,37	n.d.	1170 – 1220 C	45' – 60'
GRS-4391	Spotted effect Orange	0,08 – 0,37	n.d.	1170 – 1220 C	45' – 60'
GRS-4401	Spotted effect Beige	0,08 – 0,37	n.d.	1170 – 1220 C	45' – 60'
GRS-4411	Spotted effect Dark Beige	0,08 – 0,37	n.d.	1170 – 1220 C	45' – 60'
GRS-4421	Spotted effect Brown	0,08 – 0,37	n.d.	1170 – 1220 C	45' – 60'
GRS-4431	Spotted effect Cofee Brown	0,08 – 0,37	n.d.	1170 – 1220 C	45' – 60'
GRS-4441	Spotted effect Yellow	0,08 – 0,37	n.d.	1170 – 1220 C	45' – 60'

N B. : We recommend to perform always the preliminary tests before the production, since we are not responsible for the material accidentally damaged.
For any another technical information on the product, consult the corresponding safety data sheet.